

MATERIAL DATA



# VICTREX<sup>®</sup> PEEK

CHEMICAL RESISTANCE



# CHEMICAL RESISTANCE

## VICTREX PEEK Polymers



HIGH PERFORMANCE PEEK POLYMERS

Chemical                      23°C   100°C   200°C

ACIDS			
Acetic Acid, 10% Conc.	A	A	
Acetic Acid, Conc.	A	A	A
Acetic Acid, Glacial	A	A	
Acrylic Acid	A	A	
Aqua Regia	C	C	C
Benzene Sulfonic Acid	C		
Benzoic Acid	A	A	
Boric Acid	A	A	
Carbolic Acid	A		
Carbonic Acid	A	A	
Chloroacetic Acid	A	A	
Chlorosulfonic Acid	C	C	C
Chromic Acid, 40% Conc.	A		
Chromic Acid, Conc.	C	C	C
Citric Acid	A	A	
Formic Acid	B	B	
Hydrobromic Acid	C	C	C
Hydrochloric Acid, 10% Conc.	A	A	
Hydrochloric Acid, Conc.	A	B	
Hydrocyanic Acid	A	A	
Hydrofluoric Acid, 40% Conc.	C	C	C
Lactic Acid	A	A	
Maleic Acid	A	A	
Nitric Acid, 10% Conc.	A	A	
Nitric Acid, 30% Conc.	B		
Nitric Acid, 50% Conc.	C	C	C
Nitric Acid, Conc.	C	C	C
Nitrous Acid, 10% Conc.	A		
Oleic Acid	A		
Oleum	C	C	C
Oxalic Acid	A	A	
Perchloric Acid	A	A	
Phosphoric Acid, 10% Conc.	A	A	A
Phosphoric Acid, 50% Conc.	A	A	A
Phosphoric Acid, 80% Conc.	A	A	
Phthalic Acid	A	A	
Picric Acid	A	A	
Silicic Acid	A	A	
Sulfuric Acid, < 40% Conc.	B	B	B
Sulfuric Acid, > 40% Conc.	C	C	C
Sulfurous Acid	A	A	
Tannic Acid, 10% Conc.	A	A	
Tartaric Acid	A	A	
Trifluoromethyl Sulfonic Acid	C	C	C

Chemical                      23°C   100°C   200°C

ALCOHOLS			
Benzyl Alcohol	A		
Butanol	A		
Cyclohexanol	A		
Ethanol	A	A	
Ethylene Glycol	A	A	B
Ethylene Glycol, 50% Conc.	A	A	A
Glycerol	A		
Gylcols	A	A	
Isopropanol	A		
Methanol	A	A	
Propanol	A		
ALDEHYDES AND KETONES			
Acetaldehyde	A	A	
Acetone	A	A	
Benzaldehyde	A		
Cyclohexanone	A		
Formaldehyde	A	A	
Formalin	A		
Ketones	A		
Methylethyl Ketone (MEK)	A	B	C
N-Methyl-2-Pyrrolidone (NMP)	A		
BASES			
Ammonia 880	A		
Ammonia Anhydrous	A	A	A
Ammonia Liquid	A	A	A
Ammonium Hydroxide, 10% Conc.	A		
Ammonium Hydroxide, Conc.	A		
Calcium Hydroxide	A		
Hydrazine	A	A	
Hydroxides	A		
Magnesium Hydroxide	A		
Potassium Hydroxide, 10% Conc.	A		
Potassium Hydroxide, 70% Conc.	A		
Sodium Hydroxide, 10% Conc.	A	A	A
Sodium Hydroxide, 50% Conc.	A	A	A
Sodium Hydroxide, Conc.	A		
ESTERS			
Aliphatic Esters	A	A	
Amyl Acetate	A	A	
Butyl Acetate	A		
Dibutyl Phthalate	A		
Dimethyl Phthalate	A		
Diethyl Phthalate	A		
Ethyl Acetate	A		
Oils (Di-Ester and Phosphate Ester Based)	A	A	

Chemical 23°C 100°C 200°C

ETHERS			
Diethylether	A	A	
Dioxane	A		
Ether	A	A	
Ethylene Oxide (EtO)	A		
Tetrahydrofuran (THF)	A		
HALOGENATED ORGANICS			
1,1,1 Trichloroethane (Genklene <sup>1</sup> )	A		
1,2 Dichloroethane	A		
Carbon Tetrachloride	A	A	
Chorobenzene	A	A	
Chloroform	A	A	
Dibromoethane	A		
Dichlorobenzene	A		
Dichloroethane	A		
Ethylene Dichloride	A		
Freon <sup>2</sup> 11 Trichlorofluoromethane	A		
Freon 113 Trichlorotrifluoroethane	A		
Freon 114 1,1 Dichloro	A		
1,2,2,2 Tetrafluoroethane	A		
Freon 12 Dichlorodifluoromethane	A		
Freon 22 Chlorodifluoromethane	A	A	
Freon 134a	A		
Freon 502	A	A	
Methylene Chloride	A		
Perchloroethylene	A	A	
Trichloroethylene	A	A	
HYDROCARBONS			
Acetylene	A	A	
Aromatic Solvents	A	A	
Aviation Hydraulic Fluid	A		
Benzene	A	A	
Brake Fluid (Mineral)	A	A	A
Brake Fluid (Polyglycol)	A	A	A
Butane	A		
Crude Oil	A		
Cyclohexane	A	A	
Diesel Oil	A		
Dowtherm <sup>3</sup> A			C
Dowtherm G			B
Dowtherm HT			B
Dowtherm LF			B
Ethane	A		
Fuel Oil	A		
Gas (Manufactured)	A		
Gas (Natural)	A		
Gasoline	A	A	
Heptane	A		
Hexane	A		
Hydraulic Fluid	A		
Iso-Octane	A		

Chemical 23°C 100°C 200°C

HYDROCARBONS (CONT.)			
Kerosene	A		
Lubricating Oil	A		
Methane (Gas)	A	A	A
Motor Oil	A	A	A
Naphtha	A	A	
Naphthalene	A	A	
Oils (Petroleum)	A	A	
Oils (Vegetable)	A	A	
Pentane	A		
Petroleum Ether	A		
Propane	A		
Skydrol <sup>4</sup> Hydraulic Fluid	A		
Styrene (Liquid)	A		
Toluene	A		
Transformer Oil	A	A	
Vaseline <sup>5</sup>	A		
Xylene	A		
INORGANICS			
Aluminum Chloride	A	A	
Aluminum Sulfate	A	A	
Alum, Saturated	A	A	
Ammonium Chloride, 10% Conc.	A	A	
Ammonium Nitrate	A	A	
Antimony Trichloride	A	A	
Barium Salts (Chloride, Sulfide)	A		
Bleach	A	A	
Brine	A	A	
Bromine	C	C	C
Bromine (Dry)	C	C	C
Bromine (Wet)	C	C	C
Bromine Water, Saturated	A	A	
Calcium Bisulfide	A	A	
Calcium Carbonate	A		
Calcium Chloride	A	A	
Calcium Hypochlorite	A	A	
Calcium Nitrate	A		
Calcium Sulfate	A	A	
Carbon Dioxide (Dry)	A		
Carbon Monoxide (Gas)	A	A	A
Chlorine	C	C	C
Copper Acetate	A	A	
Copper Carbonate	A	A	
Copper Chloride	A	A	
Copper Cyanide	A	A	
Copper Fluoride	A	A	
Copper Nitrate	A	A	
Copper Sulfate	A	A	
Cupric Fluoride	A	A	
Cupric Sulfate	A	A	
Cuprous Chloride	A	A	

Chemical 23°C 100°C 200°C

INORGANICS (CONT.)			
Ethylene Nitrate	A		
Ferric Chloride	B	B	
Ferric Nitrate	A		
Ferric Oxide	A	A	
Ferric Sulfate	A		
Ferrous Chloride	A		
Ferrous Nitrate	A		
Ferrous Sulfate	A	A	
Fluorine	C	C	C
Hydrogen Peroxide	A	A	
Hydrogen Sulfide (Gas)	A	A	A
Iodine	B		
Lead Acetate	A	A	
Lime	A	A	
Magnesium Chloride	A	A	
Magnesium Sulfate	A	A	
Mercuric Chloride	A	A	
Mercurous Chloride	A		
Mercury	A	A	
Nickel Acetate	A	A	
Nickel Chloride	A	A	
Nickel Nitrate	A	A	
Nickel Salts	A		
Nickel Sulfate	A	A	
Nitrogen	A		
Nitrous Oxide	A		
Oxygen	A		
Ozone	A	B	
Phosphorous Chlorides	A	A	
Phosphorous Pentoxide	A	A	
Potassium Aluminum Sulfate	A	A	
Potassium Bicarbonate	A		
Potassium Bromide	A	A	
Potassium Carbonate	A		
Potassium Chlorate	A	A	
Potassium Chloride	A	A	
Potassium Dichromate	A		
Potassium Ferricyanide	A		
Potassium Ferrocyanide	A		
Potassium Hydroxide	A	A	
Potassium Nitrate	A	A	
Potassium Permanganate	A		
Potassium Sulfate	A	A	
Potassium Sulfide	A		
Silicone Fluids	A	A	
Silver Nitrate	A	A	
Sodium Acetate	A		
Sodium Bicarbonate	A		
Sodium Carbonate	A	A	
Sodium Chlorate	A	A	

Chemical 23°C 100°C 200°C

INORGANICS (CONT.)			
Sodium Chloride	A	A	
Sodium Hypochlorite	A	A	
Sodium Nitrate	A	A	
Sodium Nitrite	A		
Sodium Peroxide	A	A	
Sodium Salts	A		
Sodium Silicate	A	A	
Sodium Sulfate	A	A	
Sodium Sulfide	A	A	
Sodium Sulfite	A	A	
Sodium (Hot)	C	C	C
Stannic Chloride	A	A	
Stannous Chloride	A	A	
Steam	A	A	A
Sulfites	A	A	
Sulfur	A	A	
Sulfur Chloride	A	A	
Sulfur Dichloride	A	A	
Sulfur Dioxide	A	A	A
Sulfur Hexafluoride (Gas)	A		
Sulfur Trioxide	A	A	
Tar	A		
Tetraethyl Lead	A		
Water, Distilled	A	A	
Water	A	A	A
Water, Sea/Salt	A	A	
Zinc Chloride	A	A	
Zinc Sulfate	A	A	
MISCELLANEOUS			
Adhesives (not cyanoacrylates)	A		
Apple Juice	A		
Aviation Spirit	A		
Beer	A	A	
Cooking Oil	A		
Creosote	A		
Detergent Solutions (non-phenolic)	A	A	
Edible Fats and Oils	A		
Fatty Acids	A	A	
Fruit Juice	A	A	
Gelatin	A	A	
Ketchup	A		
Linseed Oil	A		
Milk	A	A	
Mineral Oil	A		
Molasses	A	A	
Olive Oil	A	A	
Peanut Oil	A	A	
Paraffin	A	A	
Sewage	A	A	

Chemical 23°C 100°C 200°C

MISCELLANEOUS (CONT.)			
Soap Solution	A		
Starch	A	A	
Tallow	A	A	
Turpentine	A		
Urea	A	A	
Varnish	A		
Vinegar	A	A	
Wax	A		
White Spirit	A		
Wines and Spirits	A		
Yeast	A	A	

Chemical 23°C 100°C 200°C

ORGANO-NITROGENS			
Acetonitrile	A		
Aniline	A	B	
Dimethyl Formamide (DMF)	A		
Diethylamine	A		
Nitrobenzene	A		C
Pyridine	A	A	
PHENOLS			
Phenol, Conc.	C	C	C
Phenol, Dilute	A		
SULFUR COMPOUNDS			
Carbon Disulfide	A	A	
Dimethylsulfoxide (DMSO)	B	B	
Diphenylsulfone (DPS)	B	C	C
Ethylene Sulfate	A		

#### KEY AND INTERPRETATION

Test bars of unfilled PEEK were immersed in chemicals at constant temperature for a minimum of 7 days (concentrated, unless otherwise stated). Chemical compatibility was assessed via retention of mechanical properties, supplemented by weight or dimensional changes when applicable. Compatibility was then classified into A, B, or C which should be interpreted as follows:

- A – No interaction. Victrex materials are likely to operate in these chemicals. It is nevertheless recommended to validate the application performance.
- B – Slight interaction. Victrex materials could be used in some applications exposed to these chemicals. It is necessary to evaluate the application specific performance criteria.
- C – Severe interaction. Victrex materials should only be considered for applications with exposure to these chemicals under exceptional circumstances.

<sup>1</sup> Genklene is a registered trademark of ICI

<sup>2</sup> Freon is a registered trademark of DuPont

<sup>3</sup> Dowtherm is a registered trademark of Dow Chemical

<sup>4</sup> Skydrol is a registered trademark of Monsanto

<sup>5</sup> Vaseline is a registered trademark of Chesebrough-Pond's, Inc.



Victrex is an innovative world leader in high performance polymer solutions with products sold under the brand names of VICTREX® PEEK, VICOTE® Coatings, APTIV® film and VICTREX Pipes™. With production facilities in the UK backed by sales and distribution centers serving more than 30 countries worldwide, our global sales and technical support services work hand-in-hand with OEMs, designers and processors offering assistance in the areas of processing, design and application development to help them achieve new levels of cost savings, quality, and performance.

[www.victrex.com](http://www.victrex.com)

#### World Headquarters

Victrex plc  
Hillhouse International  
Thornton Cleveleys  
Lancashire  
FY5 4QD  
United Kingdom

TEL +44 (0)1253 897700  
FAX +44 (0)1253 897701  
MAIL [victrexplc@victrex.com](mailto:victrexplc@victrex.com)

#### Americas

Victrex USA Inc  
300 Conshohocken State Road  
Suite 120  
West Conshohocken  
PA 19428  
USA

TEL +1 800-VICTREX  
TEL +1 484-342-6001  
FAX +1 484-342-6002  
MAIL [americas@victrex.com](mailto:americas@victrex.com)

#### Europe

Victrex Europa GmbH  
Langgasse 16  
65719 Hofheim/Ts.  
Germany

TEL +49 (0)6192 96490  
FAX +49 (0)6192 964948  
MAIL [customerservice@victrex.com](mailto:customerservice@victrex.com)

#### Japan

Victrex Japan Inc  
Mita Kokusai Building Annex  
4-28, Mita 1-chome  
Minato-ku  
Tokyo 108-0073  
Japan

TEL +81 (0)3 5427 4650  
FAX +81 (0)3 5427 4651  
MAIL [japansales@victrex.com](mailto:japansales@victrex.com)

#### Asia Pacific

Victrex High Performance  
Materials (Shanghai) Co Ltd  
Part B Building G  
No. 1688 Zhuanxing Road  
Xinzhuan Industry Park  
Shanghai 201108  
China

TEL +86 (0)21-6113 6900  
FAX +86 (0)21-6113 6901  
MAIL [scsales@victrex.com](mailto:scsales@victrex.com)

© Victrex plc March 2016

Victrex plc believes that the information contained in this brochure is an accurate description of the typical characteristics and/or uses of the product or products, but it is the customer's responsibility to thoroughly test the product in each specific application to determine its performance, efficacy and safety for each end-use product, device or other application. Suggestions of uses should not be taken as inducements to infringe any particular patent. The information and data contained herein are based on information we believe reliable. Mention of a product in this documentation is not a guarantee of availability. Victrex plc reserves the right to modify products, specifications and/or packaging as part of a continuous program of product development. VICTREX® is a registered trademark of Victrex manufacturing limited. VICTREX pipes™ is a trademark of Victrex manufacturing limited. PEEK-ESD™, HT™, ST™ and WG™ are trademarks of Victrex plc. VICOTE® and APTIV® are registered trademarks of Victrex plc. Victrex plc makes no warranties, express or implied, including, without limitation, a warranty of fitness for a particular purpose or of intellectual property non-infringement, including, but not limited to patent non-infringement, which are expressly disclaimed, whether express or implied, in fact or by law. Further, Victrex plc makes no warranty to your customers or agents, and has not authorized anyone to make any representation or warranty other than as provided above. Victrex plc shall in no event be liable for any general, indirect, special, consequential, punitive, incidental or similar damages, including without limitation, damages for harm to business, lost profits or lost savings, even if Victrex has been advised of the possibility of such damages, regardless of the form of action.

